binderholz

# binderholz **CUSTOM PANELS**

| Antique panel | |
|---|---|
| **Structure** | 3-ply spruce<br>Cover layers continuously steamed |
| **Formats** | 2.050 x 5.000 mm |
| **Thickness** | 19 mm |
| **Benefits** | Steaming the sawn timber gives the cover layer‘s lamella a warmer colour |
| **Application** | Interior fit-out - walls, ceilings, furniture |

| Thermoform panel | |
|---|---|
| **Structure** | 3-ply spruce, heat-treated |
| **Formats** | 2.050 x 5.000 mm |
| **Thickness** | 19 mm |
| **Benefits** | Dimensionally stable with low shrinkage and swelling. Practically no additional crack formation when used outside.<br>Colour coatings last longer. Largely resistant to mould and insect infestation. Durability as per EN 252 class 2 |
| **Application** | Interior fit-out, covered exterior areas |

# binderholz **CUSTOM PROCESSING**

for 1-, 3- and multi-ply panels

## EDGE PROCESSING

| Processing options | |
|---|---|
| **Tongue and groove joint with micro chamfer** |  |

## SURFACE PROCESSING

**Brushed**

On one or both sides up to a panel width of 2.050 mm

**Hewn**

On one or both sides up to a panel width of 2.050 mm

**Holes for acoustic panels**

Standard hole diameter and distance 8 x 32 mm

Formats and quantities upon request

binderholz

**Binderholz GmbH · Solid wood panel plant**

Gewerbegebiet 2 · A-5113 St. Georgen bei Salzburg

fon +43 6272 8511 · fax +43 6272 8511-12001

mhp@binderholz.com · www.binderholz.com

PEFC

PEFC/06-35-20

**Download**